

This page is mainly introduced the C35R Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of C35R, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Structure Steel C35R

	C35R Standard Number:				
ITEM Standard Number Descriptions					

C35R Chemical composition(mass fraction)(wt.%)									
Chemical Min.(%)							Max.(%)		
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Та
0.32-0.39	0.4	0.50-0.80		020-0.040	0.40	0.40	0.10		
W	N	Cu	Co	Pb	В	Nb	Al	Ti	Other

C35R

C35R Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

C3	5R Mechanical Propertie	es
Tensile strength	231-231	σb/MPa
Yield Strength	154	σ 0.2 ≥/MPa
Elongation	56	δ5≥(%)



Steel GradesC35R Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

C35R Heat Treatment Regime						
Annealing	Quenching	Tempering	Tempering Normalizing			
√	√ √		√	V		

C35R Range of products						
Product type	Products	Dimension	Processes	Deliver Status		
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,		
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED		

We can produce Structure Steel the specifications follows: