

This page is mainly introduced the XK9258S Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of XK9258S, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Structure Steel XK9258S

	XK9258S Standard Number:				
ITEM Standard Number Descriptions					

XK9258S Chemical composition(mass fraction)(wt.%)									
Chemical Min.(%) Max.(%)									
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Та
0.50-0.65	1.60-2.20	0.70-1.05	0.04	0.040					
W	N	Cu	Co	Pb	В	Nb	Al	Ti	Other

XK9258S

XK9258S Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

XK92	XK9258S Mechanical Properties				
Tensile strength	231-231	σb/MPa			
Yield Strength	154	σ 0.2 ≥/MPa			



Steel GradesXK9258S Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Elongation	56	δ5≥(%)
Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

XK9258S Heat Treatment Regime						
Annealing	Annealing Quenching Tempering Normalizing Q & T					
√	√	√	√	√		

XK9258S Range of products							
Product type	Products	Dimension	Processes	Deliver Status			
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Steel Bar	Round Bar, Flat Bar, Square Bar	Ф8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,			
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED			

We can produce Structure Steel the specifications follows: