

This page is mainly introduced the STS303Se Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of STS303Se, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Datasheet for Steel Grades Special Alloy STS303Se

### STS303Se Standard Number:

| ITEM | Standard Number | Descriptions |
|------|-----------------|--------------|
|------|-----------------|--------------|

### STS303Se Chemical composition (mass fraction) (wt.%)

| Chemical |          |          | Min.(%) |          |           |            | Max.(%)  |    |              |
|----------|----------|----------|---------|----------|-----------|------------|----------|----|--------------|
| C        | Si       | Mn       | P       | S        | Cr        | Ni         | Mo       | V  | Ta           |
| Max 0.15 | Max 1.00 | Max 2.00 | Max 0.2 | Max 0.06 | 17.0-19.0 | 8.00-10.00 | Max 0.60 |    |              |
| W        | N        | Cu       | Co      | Pb       | B         | Nb         | Al       | Ti | Other        |
|          |          |          |         |          |           |            |          |    | Se: max 0.15 |

KS standard austenite stainless steel bars (KS D3706-1992)

### STS303Se Physical Properties

|                  |         |                          |
|------------------|---------|--------------------------|
| Tensile strength | 115-234 | $\sigma_b$ /MPa          |
| Yield Strength   | 23      | $\sigma_{0.2} \geq$ /MPa |
| Elongation       | 65      | $\delta_5 \geq$ (%)      |
| $\psi$           | -       | $\psi \geq$ (%)          |
| Akv              | -       | Akv $\geq$ /J            |
| HBS              | 123-321 | -                        |
| HRC              | 30      | -                        |

### STS303Se Mechanical Properties

|                  |         |                 |
|------------------|---------|-----------------|
| Tensile strength | 231-231 | $\sigma_b$ /MPa |
|------------------|---------|-----------------|

|                |         |                                  |
|----------------|---------|----------------------------------|
| Yield Strength | 154     | $\sigma_{0.2} \geq / \text{MPa}$ |
| Elongation     | 56      | $\delta_5 \geq (\%)$             |
| $\psi$         | -       | $\psi \geq (\%)$                 |
| Akv            | -       | $Akv \geq / \text{J}$            |
| HBS            | 235-268 | -                                |
| HRC            | 30      | -                                |

### STS303Se Heat Treatment Regime

| Annealing | Quenching | Tempering | Normalizing | Q & T |
|-----------|-----------|-----------|-------------|-------|
| √         | √         | √         | √           | √     |

### STS303Se Range of products

| Product type    | Products                                 | Dimension                  | Processes                                   | Deliver Status  |
|-----------------|--|----------------------------|---|---|
| Plates / Sheets | Plates / Sheets                          | 0.08-200mm(T)*W*L          | Forging, hot rolling and cold rolling       | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Steel Bar       | Round Bar, Flat Bar, Square Bar          | $\Phi 8$ -1200mm*L         | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting,                          |
| Coil / Strip    | Steel Coil / Steel Strip                 | 0.03-16.0x1200mm           | Cold-Rolled & Hot-Rolled                    | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Pipes / Tubes   | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded           | Annealed, Solution and Aging, Q+T, ACID-WASHED                |

**We can produce Special Alloy the specifications follows:**