

This page is mainly introduced the Z7CND17-11-02 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of Z7CND17-11-02, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Specialsteel Z7CND17-11-02

Z7CND17-11-02 Standard Number:

| ITEM | Standard Number | Descriptions |
|------|-----------------|---|
| 1 | NF A 35-573 | Stainless steels for general purposes. Plates, wide strips and strips |
| 2 | NF A 35-574 | Iron and steel. Stainless steel for general purposes. Semi- finished products, bars and wire rod |
| 3 | NF A 36-209 | Iron and steel. Austenitic and austenitic-ferritic stainless steels plates for boilers and pressure vessels |
| 4 | NF A 49-244 | Steel tubes - Welded austenitic stainless and austenitic ferritic steel rolled tubes for pressure service - Dimensions, technical conditions for delivery |
| 5 | NF E 29-043 | Non alloy and alloy steel bolting for pressure equipment - Specifications |

Z7CND17-11-02 Chemical composition(mass fraction)(wt.%)

| Chemical | | Min.(%) | | | | | Max.(%) | | | |
|----------|----|---------|----|----|----|----|---------|----|-------|--|
| C | | | | | | | 0.070 | | | |
| Si | | | | | | | 0.75 | | | |
| Mn | | | | | | | 2.00 | | | |
| P | | | | | | | 0.040 | | | |
| S | | | | | | | 0.015 | | | |
| Cr | | 16.00 | | | | | 18.00 | | | |
| Mo | | 2.00 | | | | | 2.50 | | | |
| Ni | | 10.00 | | | | | 12.00 | | | |
| C | Si | Mn | P | S | Cr | Ni | Mo | V | Ta | |
| W | N | Cu | Co | Pb | B | Nb | Al | Ti | Other | |
| | | | | | | | | | | |

Non alloy and alloy steel bolting for pressure equipment - Specifications

Z7CND17-11-02 Physical Properties

| Z7CND17-11-02 Physical Properties | | |
|-----------------------------------|---------|--------------------------|
| Tensile strength | 115-234 | σ_b /MPa |
| Yield Strength | 23 | $\sigma_{0.2} \geq$ /MPa |
| Elongation | 65 | $\delta 5 \geq$ (%) |
| ψ | - | $\psi \geq$ (%) |
| Akv | - | Akv \geq /J |
| HBS | 123-321 | - |
| HRC | 30 | - |

Z7CND17-11-02 Mechanical Properties

| Z7CND17-11-02 Mechanical Properties | | |
|-------------------------------------|---------|--------------------------|
| Tensile strength | 231-231 | σ_b /MPa |
| Yield Strength | 154 | $\sigma_{0.2} \geq$ /MPa |
| Elongation | 56 | $\delta 5 \geq$ (%) |
| ψ | - | $\psi \geq$ (%) |
| Akv | - | Akv \geq /J |
| HBS | 235-268 | - |
| HRC | 30 | - |

Z7CND17-11-02 Heat Treatment Regime

| Annealing | Quenching | Tempering | Normalizing | Q & T |
|-----------|-----------|-----------|-------------|-------|
| √ | √ | √ | √ | √ |

Z7CND17-11-02 Range of products

| Product type | Products | Dimension | Processes | Deliver Status |
|-----------------|----------------------|--------------------|---------------------------------------|---|
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Steel Bar | Round Bar, Flat Bar, | $\Phi 8$ -1200mm*L | Forging, hot rolling and | Black, Rough Turning, |

| | | | | |
|---------------|--|----------------------------|-----------------------------------|---|
| | Square Bar | | cold rolling, Cast | Shot Blasting, |
| Coil / Strip | Steel Coil /Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot-Rolled | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Pipes / Tubes | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded | Annealed, Solution and Aging, Q+T, ACID-WASHED |

We can produce Specialsteel the specifications follows: