

This page is mainly introduced the A 276 304N Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of A 276 304N, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Specialsteel A 276 304N

A 276 304N Standard Number:

ITEM	Standard Number	Descriptions
1	A 276 (2010)	Stainless Steel Bars and Shapes

A 276 304N Chemical composition (mass fraction) (wt.%)

Chemical		Min.(%)		Max.(%)					
C				0.08					
Si				0.75					
Mn				2.00					
P				0.045					
S				0.03					
Cr		18.0		20.0					
Ni		8.00		10.5					
N		0.10		0.16					
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other

Stainless Steel Bars and Shapes

A 276 304N Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_5 \geq$ (%)

ψ	-	ψ ≥ (%)
Akv	-	Akv ≥ J
HBS	123-321	-
HRC	30	-

A 276 304N Mechanical Properties

Tensile strength	231-231	σ _b /MPa
Yield Strength	154	σ _{0.2} ≥ /MPa
Elongation	56	δ ₅ ≥ (%)
ψ	-	ψ ≥ (%)
Akv	-	Akv ≥ J
HBS	235-268	-
HRC	30	-

A 276 304N Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

A 276 304N Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil / Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Specialsteel the specifications follows: