

This page is mainly introduced the 40CrNi Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 40CrNi, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Structure Steel 40CrNi

	40CrNi Standard Number:				
ITEM Standard Number Descriptions					

40CrNi Chemical composition(mass fraction)(wt.%)										
Chemical Min.(%) Max.(%)										
С	Si	Mn	Р	S	Cr	Ni		Мо	V	Ta
0.37-0.44	0.17-0.37	0.50-0.80			0.45-0.75	1.00-1.4	40			
W	N	Cu	Co	Pb	В	Nb		Al	Ti	Other

40CrNi

40CrNi Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

400	40CrNi Mechanical Properties				
Tensile strength	231-231	σb/МРа			
Yield Strength	154	σ 0.2 ≥/MPa			



Steel Grades 40 CrNi Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Elongation	56	δ5≥(%)
Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

40CrNi Heat Treatment Regime						
Annealing Quenching Tempering Normalizing						
√	√	√	√	√		

40CrNi Range of products							
Product type	Products	Dimension	Processes	Deliver Status			
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Steel Bar	Round Bar, Flat Bar, Square Bar	Ф8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,			
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED			

We can produce Structure Steel the specifications follows: