

This page is mainly introduced the **BD2A Datasheet**, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of **BD2A**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Datasheet for Steel Grades Tool Steel And Hard Alloy BD2A

### BD2A Standard Number:

ITEM	Standard Number	Descriptions
------	-----------------	--------------

### BD2A Chemical composition (mass fraction) (wt.%)

Chemical			Min.(%)				Max.(%)		
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta
1.60-1.90	≤0.60	≤0.60			12.0-13.0	≤0.40	0.70-0.90	0.25-1.00	
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other
									Cu ≤ 0.20, S n ≤ 0.05

### BD2A Physical Properties

Tensile strength	115-234	σ <sub>b</sub> /MPa
Yield Strength	23	σ <sub>0.2</sub> ≥ /MPa
Elongation	65	δ <sub>5</sub> ≥ (%)
ψ	-	ψ ≥ (%)
A <sub>kv</sub>	-	A <sub>kv</sub> ≥ /J
HBS	123-321	-
HRC	30	-

### BD2A Mechanical Properties

Tensile strength	231-231	σ <sub>b</sub> /MPa

Yield Strength	154	$\sigma_{0.2} \geq / \text{MPa}$
Elongation	56	$\delta_5 \geq (\%)$
$\psi$	-	$\psi \geq (\%)$
Akv	-	$Akv \geq / \text{J}$
HBS	235-268	-
HRC	30	-

### BD2A Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

### BD2A Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	$\Phi 8$ -1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

**We can produce Tool Steel And Hard Alloy the specifications follows:**